

# Wire and Sheet Metal Gages

Equivalent thickness in decimals of an inch

Gage No.	US Standard Gage for Uncoated Hot & Cold Rolled Sheets <sup>b</sup>	Galvanized Sheet Gage for Hot-Dipped Zinc Coated Sheets <sup>b</sup>	USA Steel Wire Gage	Gage No.	U.S. Standard Gage for Uncoated Hot & Cold Rolled Sheets <sup>b</sup>	Galvanizes Sheet Gage for Hot-Dipped Zinc Coated Sheets <sup>b</sup>	USA Steel Wire Gage
7/0	—	—	.490	13	.0897	.0934	.092 <sup>a</sup>
6/0	—	—	.462 <sup>a</sup>	14	.0747	.0785	.080
5/0	—	—	.430 <sup>a</sup>	15	.0673	.0710	.072
4/0	—	—	.394 <sup>a</sup>	16	.0598	.0635	.062 <sup>a</sup>
3/0	—	—	.362 <sup>a</sup>	17	.0538	.0575	.054
2/0	—	—	.331	18	.0478	.0516	.048 <sup>a</sup>
1/0	—	—	.306	19	.0418	.0456	.041
1	—	—	.283	20	.0359	.0396	.035 <sup>a</sup>
2	—	—	.262 <sup>a</sup>	21	.0329	.0366	—
3	.2391	—	.244 <sup>a</sup>	22	.0299	.0336	—
4	.2242	—	.225 <sup>a</sup>	23	.0269	.0306	—
5	.2092	—	.207	24	.0239	.0276	—
6	.1943	—	.192	25	.0209	.0247	—
7	.1793	—	.177	26	.0179	.0217	—
8	.1644	.1681	.162	27	.0164	.0202	—
9	.1495	.1532	.148 <sup>a</sup>	28	.0149	.0187	—
10	.1345	.1382	.135	29	—	.0172	—
11	.1196	.1233	.120 <sup>a</sup>	30	—	.0157	—
12	.1046	.1084	.106 <sup>a</sup>				

<sup>a</sup> Rounded Value. The steel wire gage has been taken from ASTM A510 "General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel". Sizes originally quoted to 4 decimal equivalent places have been rounded to 3 decimal places in accordance with rounding procedures of ASTM "Recommended Practice" E29.

<sup>b</sup> The equivalent thicknesses are for information only. The product is commonly specified to decimal thickness, not gage number.